



1. THE SHAFT SHOULD BE TESTED ULTRASONICALLY TO CHECK PRESENCE OF FLANGES & MAIN CRACKS (3/4" x 19.8")

1" x 2" DEEP B.S.W. TAP HOLES BOTH SIDE

URANIUM CORPORATION OF INDIA LTD. JADUGUDA  
(A GOVT. OF INDIA, DEPARTMENT OF ATOMIC ENERGY ENTERPRISE)

TRACED	Jaduguda	6.5.72	COUNTER SHAFT FOR P.R.Y. & SEC. MILL
DRAWN	M. J. J.		
CHECKED	M. J. J.		
APPROVED	M. J. J.		
DATE	7.7.72		
PROJECTION	SCALE: 1/4" = 1"		
REVISION C	UCI/M-245/A		

REV. A. MATL. CHANGED ON 25.5.73	
REV. B. COLLAR REMOVED ON 1.10.73	
REV. C. DIMENSION CHANGED FOR P.R.Y. MILL (77.575" TO 74") 28-2-02	

FORGED ALLOY STEEL	
MATERIAL:-	EN-24
HARDENED TO BHN-220-240	

1. THE SHAFT SHOULD BE TESTED ULTRASONICALLY TO CHECK PRESENCE OF FLANGES & MAIN CRACKS (3/4" x 19.8")	
--	--